Applied Technical Services

CHEMICAL TEST REPORT

Ref. 447347 **Date** April 3, 2025

Attention: Brad Sanford

Customer: All American Manufacturing
3919 Smyrna Church Rd
Chatsworth, GA 30705

P.O.# N/A

Sample: See below

Materials Specification: N/A

Test Methods: EPA Method 3545A *Pressurized Fluid Extraction (PFE)* and EPA Method 8321B *Solvent Extractable Nonvolatile Compounds by High Performance Liquid Chromatography/ Thermospray/Mass Spectrometry (HPLC/TS/MS) or Ultraviolet (UV) Detection*

Test Results

Sample	ATS #	Results
DFE W/ THATCH	1	See Table 1

ISO 9001:2015 Registered

Prepared by: W. Carson
Senior Chemist

Approved by: Andy Waldron Digitally signed by Andy Waldron Date: 2025.04.03 15:08:53 -04'00' A. Waldron
Chemistry Manager

This report may not be reproduced except in full without the written approval of ATS. This report represents interpretation of the results obtained from the test specimen and is not to be construed as a guarantee or warranty of the condition of the entire material lot. If the method used is a customer provided, non-standard test method, ATS does not assume responsibility for validation of the method. Measurement uncertainty available upon request where applicable.

Table 1. Quantitative Results

		DFE W/ THATCH
PFOA	CAS # 335-67-1	N.D. < 100 ppt
PFOS	CAS # 1763-23-1	N.D. < 100 ppt
PFNA	CAS # 375-95-1	N.D. < 100 ppt
PFHxS	CAS # 355-46-4	N.D. < 100 ppt
PFBS	CAS # 375-73-5	N.D. < 100 ppt
HFPO-DA	CAS # 132-52-13-6	N.D. < 100 ppt

N.D. < 100 ppt – None Detected, less than 100 parts per trillion

This report may not be reproduced except in full without the written approval of ATS. This report represents interpretation of the results obtained from the test specimen and is not to be construed as a guarantee or warranty of the condition of the entire material lot. If the method used is a customer provided, non-standard test method, ATS does not assume responsibility for validation of the method. Measurement uncertainty available upon request where applicable.

CHEMICAL TEST REPORT



Figure 1

This report may not be reproduced except in full without the written approval of ATS. This report represents interpretation of the results obtained from the test specimen and is not to be construed as a guarantee or warranty of the condition of the entire material lot. If the method used is a customer provided, non-standard test method, ATS does not assume responsibility for validation of the method. Measurement uncertainty available upon request where applicable.